

## Folia magnetyczna Magneto White

### Dimensions & Tolerance:

Item	Length (m)	Width (mm)	thickness (mm)				Thickness of PVC (mm)
Size	30	610	0.40	0.50	0.60	0.70	0.1
Tolerance	0/+0.6	-1/+3	±0.04	±0.05	±0.05	±0.05	±0.01

Item	Length (m)	Width (mm)	thickness (mm)	Thickness of PVC (mm)
Size	20	1000	0.40	0.1
Tolerance	0/+0.6	-1/+3	±0.04	±0.01

Item	Length (m)	Width (mm)	thickness (mm)	Thickness of PVC (mm)
Size	15	1000	0.70	0.1
Tolerance	0/+0.6	-1/+5	±0.05	±0.01

### Magnetic Properties:

Code	Br(Gs)	Hcb(Oe)	Hcj(Oe)	(BH) <sub>max</sub> (MGOe)
NF04	≥1400	≥1000	≥1600	0.50-0.65

**Pull Strength:**

Code	Thickness (mm)	Pole pitch (mm)	Pull (g/cm <sup>2</sup> )
NF04	0.4	2.0	≥17
NF04	0.5	2.0	≥24
NF04	0.6	2.0	≥29
NF04	0.7	2.0	≥35

**Storage:**

In the surrounding temperature -20°C to +70°C within the scope of the normal work

**Storage Condition:**

25°C and 50% humidity conditions

**Shelf life:**

12 months under original packaging condition

The magnetic force is permanent and will not degrade in normal temperature without strong magnetic interference.