

## MAGNETO PLAIN (B)

magnetic foil – Magneto plain (B)

### DIMENSIONS & TOLERANCE:

ITEM	LENGTH (m)			WIDTH (mm)		THICKNESS (mm)			
	20	30	15	1020	620	0,4	0,5	0,6	0,7
Size	20	30	15	1020	620	0,4	0,5	0,6	0,7
Tolerance	0/+0.6			-1/+5	-1/+3	±0.04	±0.05		

### PULL STRENGTH:

THICKNESS (mm)	POLE PITCH (mm)	PULL (g/cm <sup>2</sup> )
0,4	2,0	≥17
0,5	2,0	≥24
0,6	2,0	≥29
0,7	2,0	≥35

### PHYSICAL DATA:

	0.40±0.04	0.50±0.05	0.60±0.05	0.70±0.05
<b>Total thickness (mm)</b>	0.40±0.04	0.50±0.05	0.60±0.05	0.70±0.05
<b>Reference Weight (g/m<sup>2</sup>)</b>	1360±136	1700±170	2040±204	2380±238
<b>Hardness (Shore D)</b>	45±5	45±5	45±5	45±5
<b>Flexibility</b>	Without cracking	Without cracking	Without cracking	Without cracking
<b>Opacity</b>	100%	100%	100%	100%

### **STORAGE:**

For reference, it works within the range of - 20 °C to+70 °C of the ambient temperature, and the customer needs to test the actual application environment

### **STORAGE CONDITION:**

25°C and 50% humidity conditions

### **SHELF LIFE:**

12 months under original packaging condition The magnetic force is permanent and will not degrade in normal temperature without strong magnetic interference.