

GRAPHICS - INK-JET DIGITAL

Issue date : 11/03/2010  
Date last modification : 12/12/2016**4-GL3A-07869 RI-JET 50 CAST GLOSS WHITE ASP33 PERMANENT  
REPOSITIONABLE GREY WKPE140 AIRFLOW****Face Material**

Gloss white CAST vinyl.

Type	CAST vinyl	
Colour and Finish	Gloss white	
Weight	70 g/m <sup>2</sup> ±10%	ISO-536
Thickness	50 µ ±10%	ISO 534-80

**Adhesive**

Solvent based permanent repositionable adhesive, featuring low initial tack with high final adhesion value, good water resistance. High adhesion on a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP). The grey pigmentation of the adhesive gives to the material excellent coverage performances. Ideal for car wrapping.

Reference	ASP33 permanent repositionable GREY	
Type	Permanent repositionable	
Min. Appl. Temp.	+10°C	
Service Temp.	-20°C/+120°C	
Shear	Very High	
Tack	3 N/inch <sup>2</sup>	
Final Adhesion	15 N/inch	

**Liner**

Type	Embossed PE coated kraft paper - Airflow texture	
Colour and Finish	White	
Weight	135 g/m <sup>2</sup> ±10%	PP-032 - ISO 536
Thickness	150 µ ±10%	ISO 534
Transparency	n.a. %	DIN 53 147-64

**Applications**

For advertising and promotional applications (window graphics, outdoor and indoor posters, billboards and signs) and for vehicle applications (for flat sided including buses, trams and taxis and for corrugated surfaces and vehicle wrapping).

**Printing Methods**

The RI-JET series of ink-jet print media gives excellent print results with UV, solvent and eco-solvent ink-jet printing. Testing for suitability between media, printers and inks is always recommended prior to use.

**Shelf life**

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.



Ritrama S.p.A.

Via Senatore Simonetta, 24  
20867 Caponago (MB) ITALY  
e-mail: info@ritrama.com  
www.ritrama.com